


Conforming to RoHS III (2011/65/EU) and ELV(2000/53/EC)

Alloy AA 6028 is developed specifically for electronics and automotive industry for machining applications and it is renowned for good machining characteristics and excellent anodizing response. Used for automotive brake components, hydraulic valve blocks and many other applications. AA 6028 alloy is a direct replacement for 6012 and 6262, where lead is replaced with tin and bismuth and retains all the technological properties of the original alloys.



Chemical Composition AA 6028

Alloy	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Pb	Each	Total	Other
AA 6028	1.00 1.30	max. 0.50	0.25 0.40	0.60 0.90	0.70 1.00	0.04 0.10	max. 0.30	max. 0.20	max. 0.05	max. 0.05	max. 0.15	Sn=0.6-0.8 Bi=0.6-0.8

Mechanical Properties AA 6028

Cold Drawn

Temper	Dimension		Rm min.		Rp _{0.2} min.		A	A (2")	HB min.
	mm	inch (")	MPa	ksi	MPa	ksi	% min.		
T6, T8	5 to 76.2	0.197 to 3	345	50	315	46	4	5	80


Extruded

Temper	Dimension		Rm min.		Rp _{0.2} min.		A	A (2")	HB min.
	mm	inch (")	MPa	ksi	MPa	ksi	% min.		
T6 T6510 T6511	20 to 150	0.788 to 5.906	310	45	260	38	8	10	80
T6 T6510 T6511	150 to 180	5.906 to 7.087	260	38	200	29	8	10	80

Comparative Characteristics AA 6028

Temper	Corrosion resistance		Cold workability	Anodizing Response	Brazeability	Weldability	
	General	Stress				Gas	Arc
T6	●●●●	●●●●●	●●●●	●●●●●	●●●●	●●●●	●●●●
T6, T6510, T6511	●●●●	●●●●●	●●●●	●●●●●	●●●●	●●●●	●●●●

Rating: ●●●●● - Excellent | ●●●● - Good | ●●● - Fair | ● - Poor



Physical Properties AA 6028

Density (g/cm ³)	2.72
Modulus of elasticity (MPa)	69990
Thermal conductivity (W/m K)	172
Coefficient of thermal expansion (25-100°) 10 ⁻⁶ /K	23.4
Electrical conductivity at 20°C (MS/m)	26 (45% IASC)